

Scan this QR code with your smartphone for:

- Product Data Sheet and SDS
- Non-English Product Information
- Additional Product Information



**Fiberlock**  
TECHNOLOGIES

Professional Products  
Professional Results

**CAUTION!**  
**KEEP OUT OF REACH OF CHILDREN.**  
Do not take internally. Close container after each use.  
Keep from freezing.  
Store between 40°F (4.5°C) and 90°F (32°C)  
24 hour Emergency "CHEM-TEL" - 1-800-255-3924

PowerStone Plus is a clear, multipurpose, waterborne acrylic primer that provides protection to a large variety of surfaces. This highly alkali resistant coating resists household cleaners, gasoline, oil and efflorescence. PowerStone Plus seals brick, block and poured concrete to reduce water penetration and prevent surface dusting and staining. PowerStone Plus can be applied to both horizontal and vertical surfaces and is ideal for use on concrete, plaster, brick, slate and stucco. Clean metal surfaces of copper and aluminum can be finished with PowerStone Plus to prevent surface oxidation.

#### SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop and HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD(5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

Remove all surface contaminants including grease, oil, rust, stains, dirt, dust, wax and mortar spatter. New concrete must cure for a minimum of 28 days prior to application of PowerStone Plus. PowerStone Plus is supplied at the proper consistency as packaged to be applied without thinning under normal environmental and application conditions.

#### APPLICATION TOOLS

Apply PowerStone Plus with brush, roller or airless spray equipment.

- Brush: Synthetic, nylon or polyester bristle
- Roller: Synthetic fiber 3/8" nap or longer
- Spray: .015 to .019 tip @ 1400-1600 P.S.I.

#### PRODUCT APPLICATION

Apply PowerStone Plus liberally, at full-strength, working the material into the pores of the surface to ensure surface is fully coated. This product is formulated for use on porous surfaces. When applied to non-porous and/or high gloss surfaces running or dripping may occur.

#### COVERAGE

- Smooth Surfaces: 250-300 ft<sup>2</sup>/gal.
- Porous Surfaces: 200-250 ft<sup>2</sup>/gal.

#### DRYING TIME @ 70°F 50% R.H

- To Touch: 1 hour
- Recoat: 2 hours

#### CLEANUP

Clean up sealer spatters and equipment immediately after use with soapy water. Dispose of waste according to all existing local, state and federal regulations.

#### PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F (32°C). Do not mix with other coatings. Do not apply when air or surface temperatures are below 50° or apply to a damp surface. Not recommended as a sealer on glazed, quarry or other ceramic type tiles. Steel troweled concrete must be etched prior to application of PowerStone Plus to insure adhesion to the concrete. Smooth concrete with a curing membrane or hardener may require abrasion to obtain proper adhesion. When applying with a sprayer, wear a NIOSH approved respirator with any R, P, N or HE filter.



# POWERSTONE PLUS

## Waterborne Acrylic Surface Conditioner - Interior & Exterior

- Highly alkali resistant
- Helps prevent surface dusting
- Reduces water vapor transmission
- Excellent primer for masonry surfaces

NET CONTENTS: 5 Gallons

For Professional Use Only

*Industrial Coatings & Primers*

**Contains:** Monoisobutanolamine (124-68-5), 2-(methylamino)-2-methyl-1-propanol (27646-80-6), 2,5,8,11-tetramethyl 6-dodecyn-5,8-diol ethoxylate (169117-72-0), Diethylene glycol monobutyl ether (112-34-5), Water (7732-18-5), 2-methyl-4-isothiazolin-3-one (2682-20-4), Magnesium chloride (7786-30-3), Magnesium nitrate (13446-18-9), 3-iodo-2-propynyl butyl carbamate (55406-53-6)

**Maximum VOC: 200 g/l**

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects, or other reproductive harm.

#### WARNING:



**Hazard Statements:**  
Causes eye irritation.  
Causes skin irritation.

#### Precautionary Statements:

**Prevention:** Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protection (eye protection, gloves) during application. When grinding/sanding dry films, wear respiratory protection.

**Response:** If on skin, wash with plenty of soap and water. If in eyes, rinse cautiously for several minutes. Remove contact lenses if present and easy to do. Continue rinsing. If inhaled, remove victim to fresh air. If exposed or concerned, get medical advice.

**Storage:** Keep closures tight and containers upright to prevent leakage. KEEP FROM FREEZING. Product is non-combustible.

**Disposal:** The coating and any contaminated diking material should be thoroughly air dried and collected into drums. The drums should be sealed and labeled and land-filled or incinerated according to local, regional and national regulations.

**Emergency Tel. No.: CHEM TEL: (U.S.): 1-800-255-3924 (Outside the U.S.): 813-248-0585**

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither ICP Construction, Inc., nor its agents shall be responsible for the use of this product or any procedures or apparatus mentioned. We recommend that the prospective user determine the suitability of PowerStone™ Plus, for each specific project and for the health and safety of personnel working in the area.

For additional information check Safety Data Sheet (SDS) or Product Data Sheet (PDS) available online at [www.fiberlock.com](http://www.fiberlock.com).

PowerStone™ Plus, the PowerStone™ Plus Logo and other marks in this literature are trademarks of ICP Construction, Inc.

**5489-5**  
**Clear**



150 Dascomb Rd.  
Andover, MA 01810  
(800) 342-3755  
[www.fiberlock.com](http://www.fiberlock.com)