



Professional Products  
Professional Results



# GRIP-TACK

## Lockdown & Adhesive

• Adhesive primer

• Demolition adhesive

NET CONTENTS: 5 Gallons

For Professional Use Only

Industrial Coatings & Primers

### PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F (32°C). Stir thoroughly. Do not add solvents, oils, or colors in oil or mix with other coatings. Do not apply when air or surface temperature is below 60°F or when drying conditions are poor. Grip-Tack will not sufficiently dry if temperatures are below 60°F and/or humidity is high. Use adequate ventilation. Store locked up. Store in corrosive resistant/container with a resistant inner liner. Keep away from incompatibles. Store in well ventilated area. Store away from foodstuffs. Keep containers. Securely sealed and protected against physical damage. Store away from sources of heat or ignition. Keep dry and protect from direct sunlight. Protect from freezing. Extremely corrosive in presence of copper, brass and stainless steel. Highly corrosive in presence of aluminum. Mild corrosive effect on bronze. Corrosive to ferrous metals and alloys. Non-corrosive in presence of glass.

### CAUTION!

#### KEEP OUT OF REACH OF CHILDREN.

Do not take internally. Close container after each use.

Keep from freezing.

Store between 40°F (4.5°C) and 90°F (32°C)

24 hour Emergency "CHEM-TEL" - 1-800-255-3924

Calculated VOC: 0 g/l

**FIBERLOCK GRIP-TACK 6408**  
**WARNING | ATTENTION**



H315 - Causes skin irritation.  
H319 - Causes serious eye irritation.

H315 - Provoque une irritation cutanée.  
H319 - Provoque une sévère irritation des yeux.

Wear protective gloves/protective clothing/eye protection/face protection.;  
See SDS for full list of P phrases

Porter des gants de protection/des vêtements de protection/un équipement de protection des yeux/du visage. Voir SDS pour la liste complète des phrases P

Specific treatment (see advice on this label); Take off contaminated clothing and wash before reuse; IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.; If eye irritation persists: Get medical advice/attention.; IF ON SKIN: Wash with plenty of soap and water; If skin irritation occurs: Get medical advice/attention.; See SDS for full list of P phrases

Traitement spécifique (voir les conseils sur cette étiquette). Enlever les vêtements contaminés et les laver avant réutilisation. EN CAS DE CONTACT AVEC LES YEUX: rincer avec précaution à l'eau pendant plusieurs minutes. Enlever les lentilles de contact si la victime en porte et si elles peuvent être facilement enlevées. Continuer à rincer. Si l'irritation oculaire persiste: consulter un médecin. EN CAS DE CONTACT AVEC LA PEAU: laver abondamment à l'eau et au savon. En cas d'irritation cutanée: consulter un médecin. Voir SDS pour la liste complète des phrases

Canadian Contact Info:  
4050-B Sladeview Crescent Suite 200  
Mississauga, ON L5L 5Y5 Canada

**WARNING:** Cancer and Reproductive Harm -  
www.P65Warnings.ca.gov

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither ICP Construction, Inc., nor its agents shall be responsible for the use of this product or any procedures or apparatus mentioned. We recommend that the prospective user determine the suitability of, for each specific project and for the health and safety of personnel working in the area.

For additional information check Safety Data Sheet (SDS) or Product Data Sheet (PDS) available online at [www.fiberlock.com](http://www.fiberlock.com).

Grip-Tack, the Grip-Tack Logo and other marks on this label are trademarks of ICP Construction, Inc.

# 6408-5 Clear



150 Dascomb Rd.  
Andover, MA 01810  
(800) 342-3755  
[www.fiberlock.com](http://www.fiberlock.com)  
Rev. 10.16.18

Grip-Tack is a high solids, water based multipurpose lockdown/adhesive for capturing and sealing residual contaminants present before, during, and after demolition or removal projects. Its unique formulation provides a soft, tacky, flexible membrane, which locks down asbestos fibers, lead paint chips and dust to insure final clearance after the removal of lead and/or asbestos. The sticky finish traps lead dust and airborne fibers making it ideal for over-coating lead paint or asbestos prior to their removal or demolition. This product is also suitable for use as a lead paint adhesive primer for use over high gloss surfaces containing lead paint.

### SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop or HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### APPLICATION TOOLS

Apply Grip-Tack with airless spray equipment.  
Spray: .017 to .021 tip @ 2500-2700 P.S.I.

### PRODUCT APPLICATION

#### LEAD BASED PAINT APPLICATION INFORMATION

Consult all related local, state and federal regulations regarding work practices and personal protection to be used prior to surface preparation, including OSHA's Lead Exposure in Construction Standard, Title 29 of the Code of Federal Regulations, Part 1926, Section 62 (29 CFR 1926.62).

PRIMER COAT FOR EVENTUAL ENCAPSULATION OF LEAD-BASED PAINT – Inspect all surfaces to be treated to insure they are clean, dry and free of all foreign matter including: dust, rust, grease, oil, mildew, glue size, calcimine, wax, soap, loose paint, etc. Patch and repair irregularities in surfaces with an appropriate patching compound. Allow to dry and wet sand smooth. Using a brush, roller or airless sprayer; apply Grip-Tack at a rate of approximately 200 sq.ft. per gallon. Grip-Tack should be coated with L-B-C Lead Barrier Compound one hour after application.

DEMOLITION ADHESIVE – Structural components previously painted with lead-based paint should be over-coated with Grip-Tack prior to their removal. Grip-Tack's outstanding adhesion and soft tacky finish traps lead dust and minimizes lead paint chip contamination. Grip-Tack should be spray applied at a rate of 100 to 200 sq.ft. per gallon over the entire component system.

LOCKDOWN – Grip-Tack will bind residual lead paint chips

and dust for final dust wipe clearance, and provide a primed surface which can be top-coated with a 100% acrylic latex paint.

### ASBESTOS APPLICATION INFORMATION

Approved respirators must be used to prevent the inhalation of asbestos fibers that may be present in the air. Careful consideration should be given to all EPA, OSHA, and State regulations in effect at the time of application.

All asbestos abatement activities must be performed in accordance with all applicable regulations including EPA, OSHA, Federal, State and Local. For more information always contact the appropriate agencies prior to beginning any abatement project.

DEMOLITION ADHESIVE – Apply Grip-Tack to all surfaces prior to demolition or component disassembly. Grip-Tack's adhesive membrane helps prevent surface particulates such as fibers and dust from becoming airborne by binding them together and locking them down to the surface. Airborne particulates will adhere to Grip-Tack's soft tacky finish to help minimize environmental contamination during demolition and component removal projects. Grip-Tack should be spray applied at a rate of 100 - 200 sq.ft. per gallon.

LOCKDOWN – Sealing microscopic residual fibers after asbestos removal is mandatory on every project. Prior to post-removal air monitoring, apply one coat to all exposed surfaces.

PULLDOWN BY MISTING – Pulldown by misting the contaminated air is an effective control technique prior to post-removal air monitoring. To pull down contaminants such as dust and free-floating asbestos fibers effectively, stand in the center of the room and hold the spray gun as close to the ceiling as possible. A mist should then be sprayed parallel to surfaces in every direction or in a circle. In containment, apply one coat to the polyethylene walls and floor.

### COVERAGE

Smooth Surfaces: 200 ft<sup>2</sup>/gal.  
Porous Surfaces: 100-200 ft<sup>2</sup>/gal.

### DRYING TIME @ 70°F 50% R.H

To Touch: 1 hour  
To Recoat: 1 hour

### CLEANUP

Clean tools and drippings with warm soapy water before coating dries. Follow equipment manufacturer's directions to clean spray equipment. Whatever cannot be saved for recovery or recycling should be disposed of according to relevant local, state and federal government regulations. Dispose container as hazardous waste.