



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dlilabs@aol.com

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252
ISO / IEC 17025 and relevant requirements of ISO 9002

December 27, 2005

Fiberlock Technologies, Inc.
150 Dascomb Road
Andover, MA 01810-5873

Att: Mr. Scott DeLeo

Re: DL-14715A
Via FAX (978) 475-6205

OBJECTIVE

To determine the water vapor transmission properties of a fungicidal coating.

PRODUCT TESTED

The coating was submitted by Fiberlock Technologies, Inc. for testing and identified as:

~~*Aftershock Fungicidal Coating, 8390 White, Lot: 92727-1945*~~

PROCEDURES

The coating was applied at 320 square feet per gallon to yield a free film of 2-mils dry film thickness. The film was allowed to dry a minimum of seven days at standard conditions before testing in accordance with procedures outlined in ASTM Method D 1653, "Water Vapor Transmission of Organic Coating Films", Method A, Condition A (Dry Cup Method, 73°F, 50% RH).

TEST RESULTS

The *Aftershock Fungicidal Coating* exhibited the following water vapor transmission properties:

Water Vapor Transmission Rate (WVT)	-	1.2 grains/square foot/hour
Water Vapor Permeance (WVP)	-	2.9 perms

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Mario Lazaro, Jr.'.

Mario Lazaro, Jr.
Assistant Technical Director

cc: T. J. Sliva